



## CommGuard™ 113B Rust Preventative



### WHAT IT DOES:

**CommGuard™ 113B Rust Preventative** is an outstanding water displacing, non-staining rust preventative that will rapidly separate water from metal surfaces after machining operations and/or alkali cleaning. **CommGuard™ 113B Rust Preventative** is concentrated and will provide extended protection.

### WHERE TO USE IT:

**CommGuard™ 113B** can be used on any metal surface after machining operations and/or alkali cleaning.

**CommGuard™ 113B** Rust Preventative can be applied by brushing, dipping or spraying. The ultra-thin film left behind will provide effective protection of ferrous and non-ferrous metals from atmospheric corrosion even under conditions of high humidity. The resultant film left behind, upon total evaporation of the carrier, should be faintly visible.

### PERFORMANCE BENEFITS:

**CommGuard™ 113B** is especially formulated to deliver the following benefits:

- Concentrated to provide extended corrosion protection.
- Protection of ferrous and non-ferrous metals from atmospheric corrosion even under conditions of high humidity.
- **CommGuard™ 113B** will easily pass the ASTM D-1748 Humidity Testing at more than 75 Hours.
- When the film is properly prepared the **CommGuard™ 113B** will pass a minimum of 3 hours neutral salt spray test as outlined in ASTM B-117.



# CommGuard™ 113B

## Rust Preventative



### TECHNICALLY SPEAKING:

Test	CommGuard™ 113B
Viscosity: cSt @ 40°C	1.7
Viscosity: SUS @ 100°F	8.0
Flash Point, COC °C	> 64
Flash Point, COC °F	> 148
Specific Gravity	0.800
Density lbs/US gallon	6.68
Melting Pt., °F Residual Film	103
Copper Corrosion, 3 Hrs., 100°C, (212°F)	1A

These are typical figures and do not constitute a specification.

### Handling & Safety Information

For information on the safe handling and use of this product, refer to the Material Safety Data Sheet obtainable from Commonwealth Oil Corporation.



**Available in Pails, Drums and One-Way Bulk Containers**

2080 FERRISS ROAD NORTH, HARROW, ONTARIO, CANADA N0R 1G0  
519-738-3503 • 800-265-3689 • FAX- 519-738-3335 [inquiries@commonwealthoil.com](mailto:inquiries@commonwealthoil.com) • [www.commonwealthoil.com](http://www.commonwealthoil.com)