



CommGuard™ 114A Rust Preventative



WHAT IT DOES:

Commonwealth Oil's **CommGuard™ 114A Rust Preventative** is an outstanding water displacing, non-staining rust preventative, that will rapidly separate water from metal surfaces after machining operations and/or alkali cleaning.

WHERE TO USE IT:

CommGuard™ 114A Rust Preventative can be applied by brushing, dipping or spraying. The ultra-thin film left behind will provide effective protection of ferrous and non-ferrous metals from atmospheric corrosion even under conditions of high humidity. The resultant film left behind, upon total evaporation of the carrier, should be faintly visible.

PERFORMANCE BENEFITS:

CommGuard™ 114A Rust Preventative has been specifically formulated to provide the following benefits:

- Rapidly separates water from metal surfaces.
- Non-staining.
- Thin film left behind to provide effective protection of ferrous and non-ferrous metals from corrosion even under conditions of high humidity.





TECHNICALLY SPEAKING:

Test	CommGuard™ 114A
Flash Point, COC °C	> 120
Flash Point, COC °F	> 248
Evaporation Rate n-BuAc=1	Slower than n-BuAc
Melting Pt., °C Residual Film	39
Melting Pt., °F Residual Film	103
Aniline Point, °C	79
Aniline Point °F	174
Vap. Press Torr @ 20°C	< 0.1
Copper Corrosion, 3 Hrs., 100°C, (212°F)	1A
Recommended Exposure Limit – ACGIH (mg/m ³)	5
Density, lbs./US Gallon	6.68
Specific Gravity	0.80

These are typical figures and do not constitute a specification.

Handling & Safety Information

For information on the safe handling and use of this product, refer to the Material Safety Data Sheet obtainable from Commonwealth Oil Corporation.



Available in Pails, Drums and One-Way Bulk Containers