



Rust Veto 113C

Rust Preventative

(Formerly Commguard 113C)

WHAT IT DOES:

Rust Veto 113C Rust Preventative is an outstanding water displacing, non-staining rust preventative that will rapidly separate water from metal surfaces after machining operations and/or alkali cleaning. **Rust Veto 113C Rust Preventative** is concentrated and will provide extended protection.

WHERE TO USE IT:

Rust Veto 113C meets the requirements of Mil-C-16173D Grade 3 and Mill-C-16173 Grade 5.

Rust Veto 113C can be used on any metal surface after machining operations and/or alkali cleaning.

Rust Veto 113C Rust Preventative can be applied by brushing, dipping or spraying. The ultra-thin film left behind will provide effective protection of ferrous and non-ferrous metals from atmospheric corrosion even under conditions of high humidity. The resultant film left behind, upon total evaporation of the carrier, should be faintly visible.

PERFORMANCE BENEFITS:

Rust Veto 113C is especially formulated to deliver the following benefits:

- Concentrated to provide extended corrosion protection.
- Protection of ferrous and non-ferrous metals from atmospheric corrosion even under conditions of high humidity.
- **Rust Veto 113C** will easily pass the ASTM D-1748 Humidity Testing at more than 1000 Hours.
- When the film is properly prepared the **Rust Veto 113C** will pass a minimum of 3 hours neutral salt spray test as outlined in ASTM B-117.
- Can impart rust protection exceeding 12 months indoors.



2080 FERRISS ROAD NORTH, HARROW, ONTARIO, CANADA N0R 1G0

519-738-3503 • 800-265-3689 • FAX- 519-738-3335 inquiries@commonwealthoil.com • www.commonwealthoil.com

Rust Veto 113C

Rust Preventative



TECHNICALLY SPEAKING:

Test	Rust Veto 113C
Viscosity: cSt @ 40°C	1.7
Viscosity: SUS @ 100°F	8.0
Flash Point, COC °C	> 64
Flash Point, COC °F	> 148
Specific Gravity	0.800
Density lbs/US gallon	6.68
Melting Pt., °F Residual Film	103
Copper Corrosion, 3 Hrs., 100°C, (212°F)	1A

These are typical figures and do not constitute a specification.

Handling & Safety Information

For information on the safe handling and use of this product, refer to the Material Safety Data Sheet obtainable from Commonwealth Oil Corporation.



Available in Pails, Drums and One-Way Bulk Containers

2080 FERRISS ROAD NORTH, HARROW, ONTARIO, CANADA N0R 1G0

519-738-3503 • 800-265-3689 • FAX- 519-738-3335 inquiries@commonwealthoil.com • www.commonwealthoil.com